



F.M.I. S.p.A.- Via Taranto, 10/12 – 25036 - S.Pancrazio di Palazzolo S/Oglio (BS) Italy  
Tel.+39-0307386033 Fax+39-0307386035  
[www.fmi-spa.com](http://www.fmi-spa.com)

PRODUCT  
REFERENCE:

## Unigraph 500®

DESCRIPTION:

**Unigraph 500®** is a new asbestos free sheet material graphite based with special polymer coating both sides.

This jointing sheet is a **PATENT** of FMI.

Anti-stick.

COLOUR

Black

SERVICE:

**Unigraph 500®** is recommended for industrial application involving high sealing stress and chemical resistance. It can be used with steam and a wide range of media (with the exception of strong oxidising agents at extreme temperature and high pressure).

It is recommended when a superior load retention at elevated temperature and an excellent creep relaxation value are required.

Thanks to its characteristics avoids flanges pitting.

Maximum temperature: 650°C (inert or reducing media)

Maximum working temperature: 450°C (oxidising media)

Minimum recommended temperature: -200°C

Maximum recommended pressure: 10 MPa (100 bar)

Note: temperatures and pressure values can not be reached simultaneously.

**MATERIAL  
COMPLIANCE  
AND APPROVALS**

KTW

**TYPICAL  
PHYSICAL  
PROPERTIES:**

Thickness:	1.50 mm
Density	1.15 g/cm <sup>3</sup>
Compressibility EN 13555	40 %
Recovery EN 13555	≥ 33 %
ASTM F152 Tensile Strength	≥ 25 MPa
Gas permeability DIN 3535-4	0,003 ml / min
ASTM OIL 3 thk increase 5 h at 150°C	2 %
ASTM FUEL B thk increase 5 h at 150°C	3.4 %
Creep Relaxation Value	< 8 %

AVAILABILITY:

Standard sheet size:	1.5 m x 1.5 m;
On request sheet size:	1,5 x 2 / 3 / 4 m
Tolerance:	+/- 50 mm
Thickness range:	0.5 to 5.0 mm
Tolerance:	+/-10%

This technical data sheet is a results of laboratory test, FMI is issuing this data sheet as a pure informative document

**Quality system accredited ISO 9001:2000**